



CS 100-FLEX

Impermeable Epoxy Membrane 100% Solid, VOC compliant

Description

CS 100-FLEX is a solventless, 100% solid, two component, epoxy-polyurethane membrane. CS 100-FLEX is a seamless impermeable membrane coating, which was specifically designed to protect substrates against water infiltration. This membrane exhibits high elongation and a high resistance to tearing. This system has been approved by the Canadian Food Inspection Agency (CFIA). It meets LEED standards.

Primary applications

- ✓ Parking deck on structural concrete slabs
- ✓ Balcony terraces
- ✓ Mechanical rooms
- ✓ Etc.

Advantages

- ✓ Contains no solvent with a very low VOC content, allowing for interior applications without harmful odors
- ✓ Impermeable and seamless
- ✓ Seamless covers can be shaped using CS 100-COVE
- ✓ Superior flexibility
- ✓ Excellent adhesive properties, allowing for application on a wide variety of substrates
- ✓ May apply several layers on itself with excellent adhesion



CS 100-FLEX

**Impermeable Epoxy Membrane
100% Solid, VOC compliant**

TECHNICAL DATA

Packaging litres / gal us			Color		
11.341 / 3	15.91 / 4.2	56.71 / 15	Part A	Part B	Mixture
Recommended Thickness			On request	Clear - Amber	On request
CS 100-FLEX	20-30 mils / 53-80 ft ² us gal 510 – 769 ml/m ²		Shelf Life		
Mix Ratio by volume			12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.		
A : B = 2 : 1					
<p><i>*Please note that the indicated mileage is calculated for flat surfaces. A porous or imperfect surface will require more material in order to cover the same mileage.</i></p>					
<p>CS 100-FLEX complies with the following LEED requirements IEQ Credit 4.2: Low emitting materials; Paints and coating SCAQMD Method 304-91 VOC content < 110 g / L</p>					
Pot life (150g)	VOC (g/litre)	Density (kg/litre)			
40 – 50 minutes 25°C	43.78	Part A	Part B	Mixture	
Solids by weight %	Recommended Thinner	Clear : 1.07-1.10	0.94 – 0.96	-	
100%	xylene				
Substrate Temperature		10°C	20°C	30°C	
Waiting Time /Overcoatability (min / max)		16 / 48	8 / 24	6 / 24	
Curing Details	Foot traffic	30 hours	24 hours	16 hours	
	Light traffic	5 days	3 days	2 days	
	Full cure and chemical resistance	10 days	7 days	5 days	
<p><i>*Note: Times and data mentioned are based on laboratory conditions. Field results may vary and will be affected by changing ambient conditions, especially changes in temperature and relative humidity.</i></p>					

PROPERTIES @ 23°C (73°F) 50% R.H.

Bond Resistance (psi) ASTM D4541	Permeability (%) ASTM D570
395 (substrate ruptures)	0.25
Hardness (Shore D) ASTM D2240	Tensile Strength (psi) ASTM D638
85-90	-



CS 100-FLEX

Impermeable Epoxy Membrane
100% Solid, VOC compliant

Compressive Strength ASTM D695	Elongation (%) ASTM D638			
-	400			
Abrasion Resistance, ASTM D4060 (CS17/1000 cycles/ 1000 g)	Viscosity @ 25 °C (cps)	Part A	Part B	Mixture
-		3000-5000	400 -600	-

SURFACE PREPARATION

The surface to be coated must be well primed. Remove dust, laitance, grease, oils, dirt, impregnating agents, waxes, foreign matter, any previous coatings, and disintegrated substances by mechanical means such as shot-blasting (BLASTRAC) or any other approved method to obtain an ICRI-CSP 3-4 profile. The compressive strength of the concrete must be at least 25 MPa (3625 lbs/in²) after 28 days and the tensile strength at least 1.5 MPa (218 lbs/in²).

MIXING

The products must be conditioned at a temperature between 18 ° C (65 ° F) and 30 ° C (86 ° F).

Pre-mixed color

Mix the resin part (A) perfectly before pouring the hardener (part B) according to the indicated mixing ratio. Depending on product amount and size of mixing equipment, mix for 1 to 3 minutes at low speed (300 to 450 rpm). During mixing, scrape the walls and bottom of the container at least once with a trowel to obtain a homogeneous mixture. As the pot life is limited, prepare amount of desired product as required in order to avoid any loss.

APPLICATION

APPLICATION : 1st coat of CS 100-FLEX

Apply the coating using a rubber squeegee and pass a roller to obtain a uniform coating.

CLEANING

Clean all application equipment with the recommended cleaner (SOLVENT 01). Once the product has hardened, it can only be removed by mechanical means. In case of skin contact, wash thoroughly with warm soapy water.



CS 100-FLEX

Impermeable Epoxy Membrane 100% Solid, VOC compliant

RESTRICTIONS

- ✓ CS 100-FLEX must be topped with a protective wear coat
- ✓ Do not apply on concrete slabs at ground level
- ✓ Do not apply at temperatures below 10 ° C / 50 ° F or above 30 ° C / 86 ° F
- ✓ The relative humidity of the surrounding work environment during the application of the coating and throughout the curing process should not exceed 85%
- ✓ Substrate temperature must be 3 ° C (5.5 ° F) above dew point measured
- ✓ Humidity content of substrate must be <4% when coating is applied
- ✓ Do not apply on porous surfaces where a transfer of humidity may occur during the application
- ✓ Protect the coating from all sources of moisture for a period of 48 hours

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Predict suitable ventilation. Consult the material safety data sheet for further information.

IMPORTANT NOTICE

The information and recommendations contained in this document are based on reliable test results according to ICR COATING SYSTEMS. The data mentioned are specific to the material indicated. If used in combination with other materials, the results may be different. It is the responsibility of the user to validate the information therein and to test the product before using it. ICR COATING SYSTEMS assumes no legal responsibility for the results obtained in such cases. ICR COATING SYSTEMS assumes no legal responsibility for any direct, indirect, consequential, economic or any other damages except to replace the product or to reimbursement the purchase price, as set out in the purchase contract.